

D'FOAM AP 910 **Foam Control Agent**

Coatings, Piment Concentartes,Printing,

Typical chemical and physical Properties

D'FOAM AP 910 is a special suitable for Aqueous Coatings based on Polyurathene dispersion & Polyurathene/ Acrylic combinations., Flexo/gravure Printing, Styrene/acrylic Emulsions. It promotes quick knock down defoaming & foam despatruaction effect in high –Viscosity medium

Solution of a polyether modified polysiloxane

PROPERTIES:

Appearance	Slightly browm Fluid
Active content	60 %
Density	0.96 to 0.99

Applications and typical treat level recommended

0.1 to 1%	:	Pigment concentrates
0.1 to 0.5%	:	Printing Inks
0.1 to 0.5%	:	Architectural & wood Coatings
0.1 to 1 %	:	Gloss and semi gloss paints

D'FOAM AP 910 can be incorporated during any stage of production. Usually 2/3 defoamer is added in the milbase and 1/3 during letdown or in the finished Paint. It is advised to incorporate under high shear forcdes to achive maximum uniform distribution.

Benefits

D'FOAM AP 910 is very active product and shows excellent performance in the control of foams and maintains flowability of the end product at desired levels (in applications such as paints and coatings).

It is very effective even at low concentrations and facilitates smoother pump operation, transport.

D'FOAM AP 910 leaves no residues in the pipes or valves of the equipment used.

Disclaimer:

All recommendations for the use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations, buyer or user remains responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility thereof. Buyer has to ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with, and subject to, our general conditions of sale and supply.

