

Coatings, Piment Concentartes, Textiles,

Typical chemical and physical Properties

D'FOAM AP W 058 is a special self-emulsifying antifoam formulation for Coatings, Pigment Concentrates, Textile Auxillaries, Cooling Lubricants and Dispersions for stripping processes., Ink formulations. During Pigment grinding & dispersion, It Promotes quick knock down defoaming.

Combination of polymethyl/dimethyl siloxane and fillers

PROPERTIES:

Appearance	Greyish translucent liquid
Active content	100 %
Viscosity at 25 °C	10 - 25 mPa.s
Flash Point	> 93 °C
Density	0.93g/cm ³ at 20 °C
pH	6 - 7

Applications and typical treat level recommended

0.2 to 1.0ml / litre of foaming media

Apply the product in its natural state by aspersion or by dosing pump and adjust the initial dosage according to the requirements.

D'FOAM AP W 058 can be added in the grinding stage. If added in the finished products, Care should be taken to ensure uniform distribution.

Benefits

D'FOAM AP W 058 is a 100% active product and shows excellent performance in the control of foams and maintains flowability of the end product at desired levels (in applications such as paints and coatings).

It is very effective even at low concentrations and facilitates smoother pump operation, transport.

D'FOAM AP W 058 leaves no residues in the pipes or valves of the equipment used.

Disclaimer:

All recommendations for the use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations, buyer or user remains responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility thereof. Buyer has to ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with, and subject to, our general conditions of sale and supply.

